

## Information about the content

<b>Responsible area:</b>	Plansee SE	<b>Prepared/Updated:</b>	See SAP-DMS
		<b>Released:</b>	See SAP-DMS
<b>Valid from:</b>	15-Jun-2021	<b>Controlled:</b>	PSE-020

This document is subject to electronic version control – confirm revision status before using.

*In doping Tungsten with Potassium, Silicon and Aluminum, the fracture behavior after process-related heat treatment is positively affected. WVMW-rods are used in high intensity discharge lamps.*

## 1 Dimensions and tolerances

### 1.1 Diameter and tolerances

Diameter <sup>a)</sup>	Tolerance
[mm]	[mm]
13,0 - 15,9	± 0,020
16,0 - 24,9	± 0,030
25,0 - 30,0	± 0,050

a) **Roundness:** Values within defined Ø-tolerance

### 1.2 Production lengths and straightness

Diameter [mm]	Production length [mm]	Straightness/ Meter [mm]
13,0 - 30,0	≥ 300	< 1,50

### 1.3 Guaranteed length tolerances in case of ordering fixed length

Nominal length [mm]	≤ 15	> 15 - 120	> 120 - 400	> 400 - 1000	> 1000 - 2000
Length tolerance [mm]	± 0,2	± 0,3	± 0,5	± 2,0	± 3,0

## 2 Physical and mechanical product properties

<b>Density:</b>	> 19,00 g/cm <sup>3</sup>
<b>Hardness:</b> a)	> 420 HV30
<b>Grain size: (ASTM E112)</b>	4 and finer

a) The actual value quoted in certificates corresponds to the mean-value of a representative control sample.

<b>Non-destructive tests:</b>	For diameter $\geq 15,0$ mm	ultrasonic testing
		eddy current testing
	For diameter $13 \geq d < 15$ mm	eddy current testing
	Visual testing	

### 2.1 Surface condition

<b>Surface</b>	<u>Centerless ground</u>
	Ra $\leq 1,0$ $\mu\text{m}$

### 3 Chemical composition

Main and minor components	Plansee		EU- Directive RoHS <sup>a)</sup>
	Min./Max. contents [µg/g] Typical	Guaranteed	
W	Balance		-
Al	16	< 30	-
K <sup>*)</sup>	-	15 – 40	-
Si	8	< 30	-
Impurities	Max. values [µg/g]		Max. values [µg/g]
	Typical	Guaranteed	
Cr	3	20	-
Cu	1	10	-
Fe	8	30	-
Mo	12	100	-
Ni	2	20	-
C	6	30	-
H	-	5	-
N <sup>**) )</sup>	1	5	-
O <sup>**) )</sup>	5	30	-
Cd	1	5	100
Hg <sup>b)</sup>	-	1	1000
Pb	1	5	1000
Cr (VI)			1000
Organic impurities (e.g. PBB, PBDE, PFOS, PFOA)	- <sup>***)</sup>	- <sup>***)</sup>	1000

a) EU-directives 2015/863/EU, 2011/65/EU and 2000/53/EC

b) Initial value

\*) Measured by Inductive Coupled Plasma-Optical Emission Spectroscopy

\*\*) Measured by Heat Extraction

\*\*\*) The presence of Cr (VI) and organic impurities can definitely be excluded because of the production process (multiple heat treatments at temperatures above 1000 °C in H<sub>2</sub>-atmosphere).

The chemical composition is checked by means of random sampling. The sampling inspection plan, analysis and evaluation methods are determined in the internal instruction PSE-020-WI-003. The application of the measured values for the chemical analysis is defined in PSE-680-WI-001.

**Remarks:** The specified physical and chemical characteristics are disclosed not regarding measurement accuracy.

### 4 Packaging, labelling, storage and certification

#### 4.1 Packaging, labelling and storage

**Standard individual packing:** rods diameter will be delivered in bundles or will be packed individually.

Each package will be provided with a label with the following information:

<b>Producer's name:</b>	Plansee
<b>Plansee order number:</b>	
<b>Lot number:</b>	
<b>Material number:</b>	
<b>Material:</b>	WVMW
<b>Dimension:</b>	Rod diameter and length
<b>Surface:</b>	
<b>Quantity:</b>	Total quantity in m or kg
<b>Date:</b>	

The material must be kept in a dry place and protected from mechanical damage. It is best to keep the material in the original packing until used.

**Special packing:** (extra costs will be invoiced)

Special packing should be used if the material is stored under unusual conditions or aggressive atmosphere (e.g. sea air, ...).

## 4.2 Inspection documents

Following inspection documents will be supplied upon customer request according to EN 10 204:

### Test report 2.2

Plansee confirms with this test report that the delivered product meets the specification and gives details of the material properties according to ongoing production surveillance, not directly related to the particular production batch.

**Inspection certificate 3.1** (extra costs will be invoiced)

An inspection officer from Plansee confirms with this inspection certificate that the delivered product meets the specification and gives test results related to the particular production batch.

## 5 Order instructions

Please quote following information when ordering:

- Product description
- Quality (the number of this specification must be mentioned)
- Diameter
- Material number
- Surface condition
- Quantity in m or kg
- Required certificate and content in case of a 3.1 inspection certificate
- **For special packing:** Specification of packaging

For further information on our delivery possibilities, please look into our <http://www.plansee.com>

## 6 Referenced standards

The standards applied for the test methods are listed in the Plansee standard InfoBase and are made available upon request.

### Changes to last version

Replacement for	Changes to last version
01	<ul style="list-style-type: none"> <li>■ Non-destructive tests:</li> </ul>

## WVMW rod



For rods  $13 \geq d < 15$  mm only eddy current testing (ultrasonic testing is not possible)

- 4.1 Packaging, labelling and storage:  
max Ø for bundle packaging deleted